

# N digiscape® wide format

W (In)	L (Ft)	Item #	Core	Product Type	Roll Wt	Rolls/ Pallet
-----------	-----------	--------	------	-----------------	------------	------------------

## DigiScape® Smooth - 9 mil FSC®

FSC Mix

54	150	DCS260-150	3"	Roll	41	30
27	20	DCS260-2720	3"	Roll	2.7	30

## DigiScape® Smooth - 17 mil ⊕ FSC®

FSC Mix, 15% Post-Consumer Recycled Fibers

54	100	DCS350-100	3"	Roll	39	30
54	300	DCS350-200	3"	Roll	117	9
27	20	DCS350-027	3"	Roll	8	30

## DigiScape® Canvas - 17 mil ⊕ FSC®

FSC Mix, 15% Post-Consumer Recycled Fibers

54	100	DCC350-100	3"	Roll	39	30
27	20	DCC350-2720	3"	Roll	8	30

## DigiScape® II Smooth - 17 mil ⊕ FSC®

FSC Mix, 38% Post-Consumer Recycled Fibers

54	100	DSII280-100	3"	Roll	44	30
54	20	DSII280-530	3"	Roll	13	30

## DigiScape® II Sand Pebble - 17 mil ⊕ FSC®

FSC Mix, 38% Post-Consumer Recycled Fibers

54	100	DSII280SP-100	3"	Roll	44	30
54	300	DSII280SP-300	3"	Roll	132	9
54	20	DSII280SP-530	3"	Roll	13	20

## DigiScape® Stick-R Smooth - 9 mil FSC®

FSC Mix

54	100	DCSRS260-100	3"	Roll	31	30
54	300	DCSRS260-300	3"	Roll	93	9
54	20	DCSRS260-5420	3"	Roll	10	30

## DigiScape® Stick-R Weave - 9 mil FSC®

FSC Mix

54	100	DCSR260-100	3"	Roll	31	30
54	300	DCSR260-300	3"	Roll	93	9
27	20	DCSR260-2720	3"	Roll	5	30

## DigiScape® FootPrint™ - 9 mil FSC®

FSC Mix

54	100	DCSFP-100	3"	Roll	31	30
27	25	DCSFP-500	3"	Roll	4	30

Paper Specifications Digiscape® Wide Format									
Caliper	Basis Weight (gsm)	Gloss @ 60°	Brightness %	Whiteness (We) %	Opacity %	Tear MD/CD**	Tensile MD/CD**	Elongation Break (MD/CD)	MIT Fold (MD/CD)
Smooth 9 pt/9 mil	260	5	92 min.	96	99.4	115/400	53/33	7/13.3	5,834/2,094
Smooth 17 pt/17 mil	370	5	90 min.	99	99.4	560/672	53/33	7/13.3	5,834/2,094
Canvas 17 pt/17 mil	370	5	90 min.	99	99.4	560/672	53/33	7/13.3	5,834/2,094
II 17 pt/17 mil	420	< 5	92 min.	96	100	26/30			
Stick-R 9 pt/9 mil	253*	5	92 min.	98	98	115/400	40/30	7/13.3	1,023/710

\*Gsm values do not include release liner | \*\*Elmendorf Tear/Grams | \*\*\* Pounds Per Inch