

# N imagease® wide format

| W<br>(In) | L<br>(Ft) | Item # | Core | Product<br>Type | Roll<br>Wt | Rolls/<br>Pallet |
|-----------|-----------|--------|------|-----------------|------------|------------------|
|-----------|-----------|--------|------|-----------------|------------|------------------|

## IMAGEase® 140 - 6 mil ⊕ FSC®

FSC Mix, 10% Post-Consumer Recycled Fibers

|    |     |                 |    |      |    |    |
|----|-----|-----------------|----|------|----|----|
| 54 | 150 | IMAGEASE140-150 | 3" | Roll | 24 | 30 |
| 60 | 200 | IMAGEASE140-650 | 3" | Roll | 34 | 30 |
| 54 | 20  | IMAGEASE140-530 | 3" | Roll | 8  | 30 |

## IMAGEase® 212 - 9 mil ⊕ FSC®

FSC Mix, 10% Post-Consumer Recycled Fibers

|    |     |                 |    |      |    |    |
|----|-----|-----------------|----|------|----|----|
| 54 | 150 | IMAGEASE212-150 | 3" | Roll | 34 | 30 |
| 60 | 200 | IMAGEASE212-650 | 3" | Roll | 48 | 30 |
| 54 | 20  | IMAGEASE212-530 | 3" | Roll | 9  | 30 |

### Paper Specifications IMAGEase® 140 Wide Format

| Caliper    | Sheffield Smoothness | Basis Weight (gsm) | Gloss @ 75° | Brightness % | Opacity % | Tear MD/CD** | Tensile MD/CD** | Wet Expansion % | Optimum Printing Conditions | Flame Classification |
|------------|----------------------|--------------------|-------------|--------------|-----------|--------------|-----------------|-----------------|-----------------------------|----------------------|
| 6 pt/6 mil | 18                   | 140                | 55          | 81           | 95        | 115/110      | 50/37           | 2               | 70°F (35-70% RH)            | ASTM-E84 Class A     |

### Paper Specifications IMAGEase® 212 Wide Format

| Caliper    | Sheffield Smoothness | Basis Weight (gsm) | Gloss @ 75° | Brightness % | Opacity % | Tear MD/CD** | Tensile MD/CD** | Wet Expansion % | Optimum Printing Conditions | Flame Classification |
|------------|----------------------|--------------------|-------------|--------------|-----------|--------------|-----------------|-----------------|-----------------------------|----------------------|
| 9 pt/9 mil | 15                   | 212                | 41          | 81           | 95        | 200/185      | 60/40           | 2.07            | 70°F (35-70% RH)            | ASTM-E84 Class A     |

\*Elmendorf Tear/Grams | \*\* Pounds Per Inch

